



## Mulco® Sealant Characteristics Charts

Solvent-Based Sealants									
	Acoustik™ 156	Butyl 124	Flex 9000™ 106	Flextra® 101	Gutter Seal 150	Pitch 136	Rapid Patch 121	Supra Expert™* 104	Zip Seal/N Peel <sup>^</sup> 141
<b>Composition</b>									
Bituminous rubber						x	x		
Butyl rubber	x	x							
Latex									
Polyurethane									
Silicone									
Thermoplastic polymers			x	x	x			x	x
<b>Characteristics</b>									
Adhesion to wet surfaces	no	no	no	no	yes	no	yes	yes	no
Elasticity	—	15%	30-40%	40-50%	25%	2%	2%	40% to 50%	—
Flammable (application)	yes	yes	yes	yes	yes	yes	yes	yes	yes
Life expectancy (depending on exposure, in years)	—	±15	±25	±30	—	±2	±2	±30	±1
Paintable (latex)	no	24 hrs.	24 hrs.	24 hrs.	24 hrs.	no	no	24 hrs.	—
Rain resistance	—	immediate	immediate	immediate	immediate	immediate	immediate	immediate	immediate
Tack-free time	—	2 hrs.	3 min.	2 min.	20 min.	24 hrs.	24 hrs.	2 min.	5 min.

<sup>^</sup>Available in 2 formulas: vanilla scent or orange (with D-Limonene\*); ecological choice)

\*This product can only be purchased through a distributor



## Mulco® Sealant Characteristics Charts

	Water-Based Sealants		
	Crack & Gap Filler & 100% Acrylic Latex 130	Latex 9000™ 137	Siliconized Latex 133
<b>Composition</b>			
Bituminous rubber			
Butyl rubber			
Latex	x	x	x
Polyurethane			
Silicone			
Thermoplastic polymers			
<b>Characteristics</b>			
Adhesion to wet surfaces	yes <sup>A</sup>	yes <sup>A</sup>	yes <sup>A</sup>
Elasticity	±8%	25%	14%
Flammable (application)	no	no	no
Life expectancy (depending on exposure, in years)	±10	±25	±10
Paintable (latex)	2 hrs.	1 hrs.	2 hrs.
Rain resistance	24 hrs.	24 hrs.	24 hrs.
Tack-free time	5 min.	10 min.	5 min.

<sup>A</sup> For temporary wet surfaces only, e.g. after cleaning

\*This product can only be purchased through a distributor

	Chemical-Based Sealants			
	Kitchen and Bathroom Silicone 113	Polyfoam 147	Supra Expert™ Foam* 105	Universal Silicone 111
<b>Composition</b>				
Bituminous rubber				
Butyl rubber				
Latex				
Polyurethane		x	x	
Silicone	x			x
Thermoplastic polymers				
<b>Characteristics</b>				
Adhesion to wet surfaces	no	yes	yes	no
Elasticity	25%	—	—	25%
Flammable (application)	no	yes	yes	no
Life expectancy (depending on exposure, in years)	—	—	—	±25
Paintable (latex)	no	24 hrs.	24 hrs.	no
Rain resistance	—	yes	yes	immediate
Tack-free time	10 min.	10 min.	10 min.	10 min.